


Crane Rail A75



R0900A	Mechanical property					Chemical composition					
	Yield strength		Tensile strength		Elongation	Hardness	C	Si	Mn	S	P
	MPa	kg/mm <sup>2</sup>	MPa	kg/mm <sup>2</sup>	min	HB				≤	≤
			880min		10%	260	0.6-0.8	0.1-0.5	0.8-1.3	0.04	0.04

