



U71Mn	Mechanical property						Chemical composition				
	Yield strength		Tensile strength		Elongation	Hardness	C	Si	Mn	S	P
	MPa	kg/mm ²	MPa	kg/mm ²	min	HB					
	460		880min		9	260	0.65-0.77	0.15-0.35	1.10-1.50	0.04	0.04